



TITAN Grey Cement In water-soluble Ecosack packaging

Pozzolanic Cement
EN 197-1 CEM IV/B (P) 32,5 R

Below you will find the recommended proportions for preparing one cubic meter of the product you require:

				
	Cement	Sand	Gravel Crushed st	Water
Concrete				
C12/15 X0	250 kg	580 lt	585 lt	200 lt
C20/25 XC1	300 kg	560 lt	600 lt	190 lt
C25/30 XS1 XS2	350 kg	520 lt	620 lt	185 lt
Screed	450 kg	880 lt	-	270 lt
High-strength Screed	625 kg	750 lt	-	310 lt
Masonry mortar	350 kg	980 lt	-	210 lt

The stated concrete categories are achieved with a deviation of +/- 3% in the material proportions, provided that the conditions for proper construction quality are maintained.

