





## TITAN Masonry Cement

Masonry Cement MC22.5

Below you will find the recommended mix proportions for preparing the desired product using 40 kg bag of Masonry Cement:

Indicative mix proportions per bag		 Sand	 Hydrated Lime Paste	 Water
Plaster - Rendering	1 bag 40kg	150 lt	-	35 lt
Masonry Mortar	1 bag 40kg	145 lt	-	35 lt
High-Strength Screed	1 bag 40kg	120 lt	-	35 lt

The stated mix proportions are indicative and may vary depending on the quality of the locally available sand.

It is not intended for use in concrete production