



## TITAN Superwhite Cement

Portland Cement  
CEM I 52,5 R

Below you will find the recommended dosages for preparing one cubic meter of the product you require:

						
	Cement	Hydrated Lime Paste	Marble Powder 1,5mm	Gravel	Sand	Water
Finishing render	200 kg	200 lt	870 lt	-	-	300 lt
C25/30 XC4 XF1	325 kg	-	-	540 lt	635 lt	170 lt
Screed	450 kg	-	-	-	950 lt	270 lt
Masonry mortar	400 kg	-	-	-	1100 lt	250 lt

The stated concrete categories are achieved with a deviation of +/- 3% in the material proportions, provided that the conditions for proper construction quality are maintained.

