



## TITAN White Cement

Portland Cement  
EN 197-1 - CEM II/ B-LL 42,5 N

Below you will find the recommended dosages for preparing one cubic meter of the product you require:

						
	Cement	Hydrated Lime Paste	Marble Powder 1,5mm	Gravel	Sand	Water
Finishing render	225 kg	185 lt	850 lt	-	-	330 lt
C20/25 XC1	300 kg	-	-	500 lt	630 lt	180 lt
Screed	450 kg	-	-	-	910 lt	270 lt
Masonry mortar	300 kg	-	-	-	1100 lt	190 lt

The stated concrete categories are achieved with a deviation of +/- 3% in the material proportions, provided that the conditions for proper construction quality are maintained.

